



**FloorMatte Satin** is an advanced floor coating specifically designed to provide a highly durable coating, without glare, for use in hospitals and long-term care facilities.

## DIRECTIONS

Read all directions and Safety Data Sheets (SDS) before using.

1. For a floor that has been stripped, properly neutralized, rinsed and allowed to dry thoroughly, apply 2-3 thin coats using a clean synthetic mop. Allow the floor to dry thoroughly between coats.
2. For a floor that has been deep scrubbed and allowed to dry thoroughly, apply 1-2 thin coats using a clean synthetic mop. Allow floor to dry thoroughly between coats.

## PRODUCT INFO

<b>Product Code</b>	114FS	114FSE	114MPE
<b>Volume</b>	2.5 US gallons	10 liters	4 liters
<b>Shipping Package</b>	2 x 2.5 gallons	2 x 10 liters	4 x 4 liters
<b>Pallet Quantity</b>	48	60	48

## SURFACES



VCT

## TECHNICAL DATA

<b>Description</b>	Polymer emulsion
<b>Appearance</b>	Milky white
<b>Specular Gloss (60°)</b> ASTM D1455-87 (2008)	<35
<b>Viscosity (Brookfield)</b> @ 68°F (20°C)	<10 centipoise
<b>Coverage Rate</b>	2500 to 3000 ft <sup>2</sup> /gal 61 to 74 m <sup>2</sup> /liter
<b>Dry Time</b>	About 30 minutes
<b>Removability</b> ASTM D1792-06	Good
<b>VOC</b> 40 CFR Part 59 Subpart C	0.02%
<b>Non-Volatile Solids</b> ASTM D2834-95 (2008)	16%
<b>Fragrance</b>	Pleasant
<b>Slip Resistance</b> ULTM410	Meets requirements
<b>Shelf Life</b> ASTM D1791-93 (2008)	1 year
<b>Density</b> ASTM D1475-98 (2008)	8.5 lb/gal @ 68°F 1.03 kg/l @ 20°C
<b>Detergent Resistance</b> ASTM D3207-92 (2008)	Excellent
<b>Freeze/Thaw</b> ASTM D3209-93 (2008)	Passes 3 cycles
<b>Container</b>	2.5 US gal/9.5 L (FS packaging) 2.64 US gal/10 L (FSE packaging) 1.06 US gal/4 L (MPE packaging)



Floor Coating and Finishing materials  
as to slip resistance only. 42E6