



Floor Finish



Pioneer Eclipse Floor Finish has 4 added advantages to help you shine - 7% higher gloss readings, 20% less drying time, less odor and improved resistance to black heel marks.

DIRECTIONS

Read all directions and Safety Data Sheets (SDS) before using.

1. For a floor that has been stripped, properly neutralized, rinsed and allowed to dry thoroughly, apply 5-6 thin coats of floor finish using a clean synthetic mop. Allow the floor to dry thoroughly between coats and prior to burnishing.
2. Optional: Apply 2 thin coats of floor sealer for old or porous floors or for high traffic areas and 4 coats of floor finish.
3. For a floor that has been deep scrubbed and allowed to dry thoroughly, apply 1-2 thin coats of floor finish using a clean synthetic mop. Allow floor to dry thoroughly between coats and prior to burnishing.

Routine Maintenance:

1. Sweep floor daily with a dust mop.
2. To clean floor use a mop or automatic scrubber with neutral cleaner.
3. Restore shine as needed with our floor maintainer.
4. Burnish as desired with ultra high speed machine and pad.
5. As needed, perform a deep scrub and re-coat applying an additional 1-2 coats of Floor Finish.
6. Allow floor to dry thoroughly between coats and prior to burnishing.
7. Strip floor when desired results cannot be achieved with routine maintenance.

PRODUCT INFO

Product Code 145MP

Volume 1 US Gallon

Shipping Packaging 4 x 1 gallons

145_PDS 12/17

SURFACES



TECHNICAL DATA

Description	Polymer emulsion
Appearance	Milky white liquid
Specular Gloss (60°) ASTM D1455-87 (2008)	> 85
Viscosity (Brookfield)	<10 centipoise
Coverage Rate	2500-3000 ft ² /gal
Dry Time	about 25 minutes
Buffability	Excellent
Removability (ASTM D1792-06)	Excellent
VOC 40 CFR Part 59 Subpart D	0.06%
Non-volatile solids ASTM D2834-95 (2008)	22%
Fragrance	slight ammonia
Slip Resistance ULTM410	meets requirements
Shelf Life ASTM D1791-93 (2008)	1 year
Density ASTM D1475-13 (2008)	8.5 lb/gal
Detergent Resistance ASTM D3207-92 (2008)	Excellent
Freeze/Thaw ASTM D3209-93 (2008)	Passes 3 cycles
Container	1 US Gallon



Floor Coating and Finishing materials
as to slip resistance only. 42E6

